

Technical Data Sheet

Issue date: 16/01/2012 Date last modification: 07/01/2019

# **GRAPHICS** - PROMOTIONAL

## 4-GL3B-02821 RI-145/80 PVC GLOSS WHITE TC9 AP900 WK135 RIT/GRY

### Face Material

Gloss white top coated soft vinyl.

Type Soft vinyl Colour and Finish Gloss white

ISO-536 Weight 110 g/m<sup>2</sup> ±10% ISO 534-80 **Thickness** 80 µ ±10%

#### Adhesive

Acrylic permanent adhesive featuring high clarity and very high cohesion. Designed for a wide variety of substrates such as glass, ABS, PS, PVC. Unsuitable for apolar surfaces (like PE and PP).

Reference **AP900** 

Type Acrylic permanent

+10°C Min. Appl. Temp. -30°C/+120°C Service Temp. Shear Very High

FINAT FTM9 7 N/25mm Tack Final Adhesion 9 N/25mm FINAT FTM2

This adhesive complies with FDA 175.105.

## <u>Liner</u>

Type One side siliconised clay coated

Kraft

Colour and Finish White

PP-032 - ISO Weight 135 g/m<sup>2</sup>

±10%

ISO 534 **Thickness** 145 µ ±10% DIN 53 147-64 Transparency n.a. %

### **Applications**

Labels, stickers and point of sale advertising with medium outdoor durability.

### **Printing Methods**

Material specifically developed for oxidative offset printing. Other printing methods: solvent based and UV screenprinting, UV offset.

Testing for suitability between media, printers and inks is always recommended prior to use.

### Shelf life

24 months, applicable only to the material delivered by Ritrama which has not undergone further processing, under the following STORAGE CONDITIONS:

- This material must be stored at a temperature of  $22^{\circ}C \pm 2^{\circ}C$  and  $50 \pm$ 5% of Relative Humidity.
- Storage area must be dry and clean.
- Keep the material in the original packaging when not used in order to protect it from dust and contamination.
- Do not expose to direct sunlight or heat sources.

All Ritrama products are subject to strict manufacturing controls to guarantee good quality products. The above information is based on research believed to be reliable, but does not constitute a warranty. All material should be tested by the purchaser to determine suitability of the product for their purposes. All information is subject to change without prior notice.



