

GRAPHICS - PROMOTIONAL

Issue date : 16/07/2010 Date last modification : 07/01/2019

4-GL3B-02822 RI-205/80 PVC GLOSS CLEAR TC9 AP900 WK135 RIT/GRY

Face Material

Gloss clear top coated plasticised vinyl film, with good flexibility and conformability on curved surfaces.

Type Colour and Finish Weight Thickness Soft vinyl Gloss clear 104 g/m² ±10% ISO-536 80 µ ±10% ISO 534-80

Adhesive

Acrylic permanent adhesive featuring high clarity and very high cohesion. Designed for a wide variety of substrates such as glass, ABS, PS, PVC. Unsuitable for apolar surfaces (like PE and PP).

Reference	AP900		
Туре	Acrylic permanent		
Min. Appl. Temp.	+10°C		
Service Temp.	-30°C/+120°C		
Shear	Very High		
Tack	7 N/25mm FINAT FTM9		
Final Adhesion	9 N/25mm FINAT FTM2		

This adhesive complies with FDA 175.105.

<u>Liner</u>

Туре	One side siliconised clay coated Kraft	
Colour and Finish Weight	White 135 g/m ²	PP-032 - ISO
Thickness	±10% 145 μ ±10%	536 ISO 534
Transparency	n.a. %	DIN 53 147-64

Applications

Promotional labels, window stickers.

Printing Methods

Material specifically developed for oxidative offset printing. Other printing methods: solvent based and UV screenprinting, UV offset. Testing for suitability between media, printers and inks is always recommended prior to use.

Shelf life

24 months, applicable only to the material delivered by Ritrama which has not undergone further processing, under the following **STORAGE CONDITIONS**:

- This material must be stored at a temperature of $~22^\circ\text{C}$ $\pm~2^\circ\text{C}$ and 50 $\pm~5\%$ of Relative Humidity.
- Storage area must be dry and clean.
- Keep the material in the original packaging when not used in order to protect it from dust and contamination.
- Do not expose to direct sunlight or heat sources.

All Ritrama products are subject to strict manufacturing controls to guarantee good quality products. The above information is based on research believed to be reliable, but does not constitute a warranty. All material should be tested by the purchaser to determine suitability of the product for their purposes. All information is subject to change without prior notice.



Ritrama S.p.A. Via Senatore Simonetta, 24 20867 Caponago (MB) ITALY e-mail:info@ritrama.com w w w . r i t r a m a . c o m

