

## description

Extra white ultra-fine papers and boards with a very smooth and velvety surface. Clear look-through. Made of pure E.C.F. pulp, certify FSC. Substances over 230 gsm are on-machine laminated in the formation stage. Characteristics provide perfect on-press performance, excellent ink-yield and brilliant printed results. In 45x64 size the substances 85gsm 100gsm and 115gsm are produced in "Litholaser" version, therefore suitable for offset pre-printing and subsequent printing on toner-based laser printers.

range

size grain substance

45x64 LG 85 100 115 230 270 300 340

64x88 LG 85 100

71x100 LG 85 100 115 140 160 190 230 270 300 340

technical features
ref. standard/instrument
unit of measure

substance	VSA	opacity	roughness	tensile strength	
ISO 536	ISO 534	ISO 2471	ISO 8791-2	ISO 1924	
g/m²	cm³/g	%	ml/min	KN/m	
				long±10%	cross±10%
85 ± 3%	1,05	88 ± 2	70 ± 20	5,2	3,2
100 ± 4%	1,05	90 ± 2	70 ± 20	5,9	3,9
115 ± 4%	1,05	92 ± 2	70 ± 20	7,2	4,2
140 ± 4%	1,05	94 ± 2	70 ± 20	8,5	4,5
160 ± 5%	1,05	_	70 ± 20	9,1	5,2
190 ± 5%	1,05	_	70 ± 20	10,4	5,9
230 ± 5%	1,05	_	60 ± 20	13,7	7,2
270 ± 5%	1,05	_	60 ± 20	15	7,8
300 ± 5%	1,05	_	60 ± 20	16,3	8,5
340 ± 5%	1,05	_	60 ± 20	_	_

Brightness (col. Extra White) - ISO 2470 (R457) - 112% ± 2 Relative Humidity 50% ± 5 ref. TAPPI 502-98

ecological features



ELEMENTAL CHLORINE FREE







The mark of responsible forestry

notes

The product is completely biodegradable and recyclable. Special runs available upon request.



Envelopes available on stock.

The Company reserves the right to modify the technological features of the product in relation to market requirements.



Splendorgel E.W. is excellent for packaging, coordinated graphic materials, labels, covers, inserts, de luxe brochures. In versions 85-100 gr. it is particolarly suitable for letterheads and writing papers.

applications

Can be used without problems with the main printing systems: letterpress, offset, blind embossing, hot foil stamping, thermography and screen printing. The macro-porous surface suggests the use of oxidative drying inks. Good chromatic and tone performance, ink load, dot gain and printing contrast are at the highest levels obtainable from uncoated papers.

printing suggestions

Varnishing and plastic laminating must be assessed in advance. The varnishing coated with an offset machine is almost fully absorbed and therefore does not improve gloss or protection. Screen-printing varnishing achieves better results, although it is often necessary to perform two shots to achieve a distinctly evident result. The surface roughness typical of uncoated papers may give rise to micro defects with plastic laminating caused by incomplete adhesion of the film to the substrate.

converting suggestions

Good results with major processing operations such as: cutting, die-cutting, scoring, folding and glueing.

